



## Fleximake Pty Ltd

A.B.N 55 146 538 301  
 19 ZILLA COURT, DANDENONG SOUTH. VIC 3175. AUSTRALIA  
 Telephone: (03) 8772 2228 | 1300 195 295  
 Fax: (03) 8774 7772  
 Email: [sales@fleximake.com.au](mailto:sales@fleximake.com.au)  
 Web: [www.fleximake.com.au](http://www.fleximake.com.au)

### Material Data Sheet

#### UCB1100 – RPVC 1100gsm

#### Unicoat Gloss 1100gsm

Properties Test Standard	Typical Characteristics	
	Metric Units	English Units
Total Weight DIN EN ISO 2286-2	1100 g/m <sup>2</sup>	32.4 oz/sq.y
Yarn (W/F) DIN EN ISO 2060	1000/ 1000 Denier	1100/ 1100 Dtex
Threads(W/F) DIN EN ISO 1049-2	12/ 12 Per cm	30/ 30 Per inch
Tensile Strength(W/F) DIN 53354	4312/ 3822 N /5cm (440/ 390 Kg/5cm)	492/ 436 lbs/inch
Tear Resistance(W/F) DIN 53363	509.6/ 470 N (52/ 48 Kg)	115/ 106 Lbs
Welding Adhesion DIN 53357	196 N /5cm (20 Kg/5cm)	22.3 lbs/inch
Temperature Resistance DIN 53361	-30°C to +70 °C	
Flame Retardant NFPA-701,DIN4102-B1,NFP92-507 M2	Optional	
Environmental EN-71, 6P, ROHS, REACH	Optional	

The above data was provided by our material manufacturer. This product data sheet is subjected to revisions once additional know-how is gained. We make no guarantee of results and assume no obligation liability whatsoever in connection with this information.



## Fleximake Pty Ltd

A.B.N 55 146 538 301  
 19 ZILLA COURT, DANDENONG SOUTH. VIC 3175. AUSTRALIA  
 Telephone: (03) 8772 2228 | 1300 195 295  
 Fax: (03) 8774 7772  
 Email: [sales@fleximake.com.au](mailto:sales@fleximake.com.au)  
 Web: [www.fleximake.com.au](http://www.fleximake.com.au)

### Fluid Resistance Guidelines (RPVC)

#### Rating Description

- E = Resistant (Good for continuous exposure)
- G = Good for intermittent exposure
- F = Use only where limited life is acceptable
- X = Do not use

Fluid	Concentration (%)	Rating
ASTM® Fuel A		F
ASTM® Fuel B		X
ASTM® Oil No. 1		G
ASTM® Oil No. 3		F
Acetate Solvents		X
Acetic Acid (Glacial)		F
Acetic Acid	40	G
Acetic Acid	10	G
Acetic Anhydride		X
Acetone		X
Acrylonitrile		E
Alcohols (Aliphatic)		F
Alkalies		E
Aluminum Salts		E
Aluminum Chloride		E
Aluminum Sulfate (Alums)		E
Ammonia (Dry Gas)		E
Ammonia (Anhydrous Liquids)		X
Ammonia (Aqueous)		E
Ammoniated Latex		E
Ammonium Chloride		E
Ammonium Chloride	10	E
Ammonium Hydroxide		E
Amyl Acetate		X
Aniline		E
Aniline Oils		X
Animal Fats & Oils		E



## Fleximake Pty Ltd

A.B.N 55 146 538 301  
 19 ZILLA COURT, DANDENONG SOUTH. VIC 3175. AUSTRALIA  
 Telephone: (03) 8772 2228 | 1300 195 295  
 Fax: (03) 8774 7772  
 Email: [sales@fleximake.com.au](mailto:sales@fleximake.com.au)  
 Web: [www.fleximake.com.au](http://www.fleximake.com.au)

Anthracene		X
Aromatic Fuels		X
Aromatic Hydrocarbons		X
Asphalt		X
Banana Oil X		X
Barium Chloride		E
Barium Hydroxide		E
Barium Sulfide		E
Benzene		X
Benzine (Petroleum Ether)		F
Borax		E
Bordeaux Mixture		E
Boric Acid		E
Brine		E
Bromine		X
Butyl Acetate		X
Butyl Alcohol		G
Calcium Chloride	20	E
Calcium Chloride	10	E
Calcium Hydroxide		E
Calcium Hypochlorite		E
Carbolic Acid (Phenol)		G
Carbon Dioxide		E
Carbon Disulfide		X
Carbon Tetrachloride		X
Carbonic Acid		E
Casein		E
Castor Oil		E
Caustic Soda		E
Chlorine (water solution)	40	F
Chlorine Gas (dry & wet)		X
Chlorobenzene		X
Chloroform		X
Chromic Acid	40	F
Chromic Acid	10	G
Chromic Acid	1	E
Citric Acid		E
Coal Tar		X
Coconut Oil		F
Corn Oil		E
Cottonseed Oil		F
Creosote		X
Cresol		F



## Fleximake Pty Ltd

A.B.N 55 146 538 301  
 19 ZILLA COURT, DANDENONG SOUTH. VIC 3175. AUSTRALIA  
 Telephone: (03) 8772 2228 | 1300 195 295  
 Fax: (03) 8774 7772  
 Email: [sales@fleximake.com.au](mailto:sales@fleximake.com.au)  
 Web: [www.fleximake.com.au](http://www.fleximake.com.au)

Cresylic Acid		X
Cyclohexane		G
Cyclohexanone		G
DDT Weed Killer		E
Degreasing Fluids		X
Detergents (dish washing)		E
Di Iso Cyante		F
Di Methyl Formamide		X
Di Methyl Hydrazine		X
Di-isodecyl Phthalate		X
Dibutyl Phthalate		X
Dichloroethylene		X
Diesel Fuel		X
Diesel Oils		F
Diethyl Ether		E
Diethylene Glycol		G
Diocetyl Phthalate (DOP)		X
Dow General Weed Killer (H2O)		G
Dow General Weed Killer		X
Esters		X
Ether		X
Ethyl Acetate		X
Ethyl Alcohol (Ethanol)		F
Ethylene Dichloride		X
Ethylene Glycol	50	G
Ethylene Oxide		X
Fatty Acids		E
Ferric Chloride		E
Ferric Sulfate		E
Ferrous Chloride		E
Ferrous Sulfate		E
Formaldehyde	40	X
Formic Acid	10	E
Freons		X
Fuel Oil		G
Furfurool		F
Gallic Acid		E
Gasoline - 100 Octane		F
Glycerine		E
Grease		E
Green Sulfate Liquor		E
Heptachlor in Petroleum		E
Heptane		F



## Fleximake Pty Ltd

A.B.N 55 146 538 301  
 19 ZILLA COURT, DANDENONG SOUTH. VIC 3175. AUSTRALIA  
 Telephone: (03) 8772 2228 | 1300 195 295  
 Fax: (03) 8774 7772  
 Email: [sales@fleximake.com.au](mailto:sales@fleximake.com.au)  
 Web: [www.fleximake.com.au](http://www.fleximake.com.au)

Hexane		F
Hydraulic Fluids - Ester Base		X
Hydraulic Fluids - Petroleum		F
Hydrobromic Acid		E
Hydrochloric Acid (Muriatic)	40	F
Hydrochloric Acid	10	G
Hydrochloric Acid	1	E
Hydrofluoric Acid	70	X
Hydrofluoroboric Acid	40	F
Hydrofluoroboric Acid	10	G
Hydrogen Peroxide	30	G
Hydrogen Peroxide	10	E
Hydrogen Peroxide	2	E
Isooctane		F
Isopropyl Acetate		X
Isopropyl Alcohol		G
Jet Fuels (JP-3, 4, and 5)		F
Kerosene		F
Ketones		X
Lacquer Thinners		X
Linseed Oil		E
Lubricating Oils, Greases, Soaps		E
Magnesium Chloride		E
Magnesium Hydroxide	10	E
Magnesium Sulfate		E
Malathion 50 in Aromatics		X
Malic Acid		E
Methyl Acetate		X
Methyl Alcohol		F
Methyl Bromide		X
Methylene Chloride		X
Methyl Ethyl Ketone		X
Methyl Isobutyl Ketone		X
Mineral Oil		E
Monochlorobenzene		X
Naphtha		F
Naphthalene		X
Nitric Acid		X
Nitric Acid	70	F
Nitric Acid	35	G
Nitric Acid	10	E
Nitrobenzene		X
Nitropropane		X



## Fleximake Pty Ltd

A.B.N 55 146 538 301  
 19 ZILLA COURT, DANDENONG SOUTH. VIC 3175. AUSTRALIA  
 Telephone: (03) 8772 2228 | 1300 195 295  
 Fax: (03) 8774 7772  
 Email: [sales@fleximake.com.au](mailto:sales@fleximake.com.au)  
 Web: [www.fleximake.com.au](http://www.fleximake.com.au)

Oleic Acid		E
Oleum		X
Oxalic Acid		E
Paint		X
Paint Thinners		X
Palmitic Acid		E
Pentachlorophenol Oil		G
Pentane		F
Perchloric Acid	70	X
Perchloric Acid	10	E
Perchloroethylene		X
Petroleum Ether		F
Phenol		G
Phosphoric Acid	85	E
Phosphoric Acid	50	E
Phosphoric Acid	10	E
Photographic Developer		E
Phthalates		X
Pitch		G
Potassium Hydroxide	50	E
Potassium Hydroxide	10	E
Power Steering Fluid		X
Propane		E
Propyl Alcohol		G
Propylene Glycol		E
Pydraul		X
Ritchfield "A" Weed Killer		F
Seawater		E
Silicone Oil		E
Silver Nitrate		F
Skydrol Oil - Type B		X
Sodium Cyanide		E
Sodium Hydroxide		G
Sodium Hydroxide	50	E
Sodium Hydroxide	10	E
Sodium Hypochlorite	PH13	G
Solvesso		X
Soybean Oil		F
Stoddard Solvent		X
Styrene		X
Sulfur Dioxide (Liquid)		X
Sulfuric Acid		X
Sulfuric Acid	75	F



## Fleximake Pty Ltd

A.B.N 55 146 538 301  
 19 ZILLA COURT, DANDENONG SOUTH. VIC 3175. AUSTRALIA  
 Telephone: (03) 8772 2228 | 1300 195 295  
 Fax: (03) 8774 7772  
 Email: [sales@fleximake.com.au](mailto:sales@fleximake.com.au)  
 Web: [www.fleximake.com.au](http://www.fleximake.com.au)

Sulfuric Acid	60	G
Sulfuric Acid	40	E
Sulfuric Acid	25	E
Sulfuric Acid	10	E
Sulfurous Acid	40	G
Tall Oil X		X
Tannic Acid		E
Tetra Ethyl Lead		X
Tetra Hydro Furan		X
Toluene		X
Toluol		X
Trichlorethane		X
Trichlorethylene		X
Tricresyl Phosphate (Skydrol)		X
Triethanol Amine		F
Trisodium Phosphate		E
Tung Oil		F
Turpentine		F
Varsol		X
Vegetable Oils and Juices		E
Vinegar		E
Vinyl Chloride		X
Water		E
Wood Preservatives		X
Xylene		X
Xylols X		X
Zinc Chloride		E
Zinc Sulfate		E

The data above is intended to serve only as a guide. No performance warranty is intended or implied. The degree of chemical attack on any material is governed by the conditions under which it is exposed. Exposure time, temperature, and size of the area of exposure usually varies considerably in application, therefore, this table is given and accepted at the user's risk. Confirmation of the validity and suitability in specific cases should be obtained.

When considering RPVC for specific applications, it is suggested that a sample be tested in actual service before specification. Where impractical, tests should be devised which simulate actual service conditions as closely as possible.